

SATEN gypsum skim coat

Product description:

SATEN is a fine gypsum-based skim coat compound for manual application on different types of substrates. It provides smooth and high-quality surface of interior walls and ceilings, ready for finishing coatings and decorations.



Standard Classification:

In compliance with EN 13279-2:2014



Advantages:

- ✓ Perfect for delicate skim coating of different surfaces
- ✓ Creates perfectly smooth surface
- ✓ Fills minor damages to 5 mm and cracks on plasterboards or other surfaces
- ✓ Economical because of the thin layer that has to be laid

Application:

- ✓ Suitable for complete plastering
- ✓ Filling in to small gaps and overhauls

Technical data

Time for work	~ 60 minutes	
Consumption	~ 0.85 kg/m ² /1mm	
Coverage	~ 11 m ² / 5 kg	~ 29 m ² / 25 kg
Mixing ratio	~ 7.5 l water : 10 kg	~ 18 l water : 25kg
Application temperature	5° - 30 ° C	
Bond strength	0.5 MPa	
Subtlety – residue retained on sieve 200 µm	1.4 %	
Reaction to fire	A1	
Expiry date	6 months	

Instructions for use:

1. **Pre-treatment of substrate:** The substrate surface has to be clean, dust-free and oil-free! Coatings without bearing capacity must be removed. Strong or weak hygroscopic substrates have to be primed in advance with a suitable primer to control absorbency and adhesion.
2. **Mixing:** Fill a very well cleaned, non-metallic container partially with water. Add to it the required amount of SATEN (18 litres of water to a bag of 25 kg) slowly and gradually, so that the level of the gypsum mixture reaches 1-2 mm above water level. Let the material settle for 3-5 minutes. Then stir the mixture by hand using a trowel or mixer (400-600 rpm) until a homogeneous mixture without lumps is formed.
3. **Skim coating in three steps:**

1) Laying a first layer

A layer with a thickness of 1 to 3 mm has to be laid. Movement of the plastering trowel has to be from the bottom upwards, with an inclination of around 30% in relation to the base. Start leveling the wall by circular movements only in one direction (or only to the left or to the right, in no case in a full circle). Wait until the skim coat is half hardened, and then process it with a clean mortar board until the surface becomes perfectly smooth. With each movement, the mortar board has to be cleaned of the picked material with a putty knife.

2) Laying a second layer

Apply a second coat of mixture after the first coat has dried completely. Lay in the same way, but with a little more pressure in order to reach an average thickness of the layer not more than 1 mm. Smooth all concavities and holes with one or two additional movements. If necessary, you can add more ready for use mixture. If necessary, polish the layer with a fine sandpaper after hardening. Polish protruding bumps carefully, and fill concave zones with a putty-knife and ready for use mixture, and repeat the procedure.

3) To reach a smooth, mirror-like surface, lay a third layer with thin consistence and skim the whole surface.

Special notes:

- ✓ It is mandatory to use perfectly clean instruments without traces of rust. Otherwise, the characteristics of the products and its bonding time can be substantially changed.
- ✓ Avoid drastic temperature changes during ventilation of workrooms.

Packaging and Storage

- ✓ 10 kg paper bags. 60 bags in a pallet. Pallet weight 600 kg.
- ✓ 25 kg paper bags. 40 bags in a pallet. Pallet weight 1000 kg.
- ✓ Store and transport it in a tightly sealed original packaging in closed, dry and ventilated areas.
- ✓ The product is suitable for use within 6 months after the production date.
- ✓ The properties of the product are guaranteed only when the product is stored and used in the right way.
- ✓ If the product becomes moist, hardened lumps will develop, which deteriorates its properties and shortens the bonding time.

Safety recommendations:

- ✓ Product not classified as hazardous.
- ✓ It is recommended to use safety gloves, mask and glasses when apply the product to prevent the risk of inhalation, irritation of the skin and eyes.

Technogips Pro reserves the right to change any of the specifications and technical data mentioned in the Technical Data Sheets at its sole discretion without prior notification. July 2019©